

**Product Data Sheet**

**NITRILE EXAMINATION GLOVE**

<b>Material</b>	: 100% Nitrile (Acrylonitrile-butadiene)
<b>Appearance</b>	: Powder free, non-sterile
<b>Thickness &amp; Colour</b>	: 3.4g Comm Flower Blue
<b>Surface</b>	: Finger textured

**Dimension**

Size	Length (mm)	Circumference (mm)	Wrist (mm)
Extra-Small	70 - 80	240 (min.)	9" 2.5 MIL-NPF-CFB 00
Small	81 - 90	240 (min.)	9" 2.5 MIL-NPF-CFB 01
Medium	91 - 100	240 (min.)	9" 2.5 MIL-NPF-CFB 02
Large	101 - 110	240 (min.)	9" 2.5 MIL-NPF-CFB 03
Extra-Large	111 - 120	240 (min.)	9" 2.5 MIL-NPF-CFB 04

**Thickness**

Point of Thickness Measurement	Thickness (mm)
Cuff	0.05 (min.)
Palm (at center of palm)	0.06 (min.)
Finger (at 13mm + 3mm from the extreme tip)	0.09 (min.)

**Physical Properties**


Criteria	Before Aging	After Aging
Tensile Strength (MPa)	≥ 14	* 14
Elongation (%)	500 (min.)	400 (min.)

- Powder Residue** : Contains less than 2 mg per glove.
- Design Feature** : Ambidextrous, straight fingers, finger textured and beaded cuff.
- Product Conformance** : Conform to ASTM D6319
- Packing** : 100 gloves per dispenser box and 10 dispensers per carton.

**Pre-shipment**

Criteria	Acceptance	Rejection
Dimension	13	ASTM S2 AQL 4.0
Physical Properties	13	ASTM S2 AQL 4.0
1000 ml Water Leak Test	G-1	1.5
Visual Inspection for Major Defects	G-1	2.5
Visual Inspection for Minor Defects	G-1	4.0

**Quality Assurance** : Manufacturing process in compliance with ISO 9001 & ISO 13485 Quality Management System.

Prepared By	Approved By
	
Josephine (QI Officer)	Cheong Kin Fu (QA Manager)

The data in above tables represent typical of the glove at time of publication and not to be used as actual product specifications.